
BND001PTB101
Data Sheet

BONDS®

STRUCTURE

Total Thickness	1.40	mm
No. of Plies	1	
Fabric	Cotton-Polyester	
Weft	Rigid	
Weight	1.40	kg/m2
Constant Temp. °C	- 10 / 90	
Intermittent Tem. °C	- 15 / 110	
1 Top cover		
Thickness	-	mm
Material	Cotton-Polyester	
Colour	Natural	
Surface	Textured	
Hardness	0	°ShA
2 Internal cover		
Material	-	
3 Bottom cover		
Thickness	0.30	mm
Material	PU	
Colour	White 00	
Surface	Pattern Y1	
Hardness	86	°ShA



PROFILES APPLICATION

Profiles on top cover	Yes
Profiles on bottom cover	Yes
Runer sidewalls	No

SPECIAL CHARACTERIST.

- FDA — FDA Food Grade
- A — Animal Oils & Grease Resistant
- V — Vegetal Oils & Grease Resistant
- LF — Low Friction


TENSIONS

	N/mm
Breaking load	60
Working load 1% elong.	3
Max. load at 1.5% elong.	4.5

SUPPORT SURFACE

Slider bed	Yes
Rollers	Yes
Trough application	No

MIN. DRUM DIA.



	mm
Flexing (F)	15
Back flexing (C)	15

FRICTION COEFF. BOTTOM COVER

On steel Din./Est.	0.60 / 0.65
On wood Din./Est.	0.65 / 0.70
On plastic Din./Est.	0.70 / 0.73

FASTENERS


25LL


REMARKS

Longitudinal splice	No
Max. manufacturing width	3000 mm
Last modified	2022.05.25

SPLICING PARAMETERS

Splice	Pressure Kp/cm2	Sup. Temp. °C	Inf. Temp. °C	Min Time	Top Cov. Flomil/ Film	Intern. Flomil	Sheet
DS/2	2.50	150	150	3	-	-	18
DS	2.00	150	150	1	-	-	2





The splice parameters are for orientation only as they depend on the type of press and the thickness of the plates used.

We recommend carrying out a trial run with pieces of the same belt before splicing the belt itself.

Time starts when the press has reached the stated temperature.

www.bondspowertransmission.com | all right reserved