
BND001PTB185
Data Sheet

BONDS®

STRUCTURE

Total Thickness	1.30	mm
No. of Plies	1	
Fabric	Polyester	
Weft	Rigid	
Weight	1.20	kg/m2
Constant Temp. °C	- 5 / 80	
Intermittent Tem. °C	- 15 / 100	
1 Top cover		
Thickness	0.70	mm
Material	PVC	
Colour	Black 01	
Surface	Pattern D	
Hardness	80	°ShA
2 Internal cover		
Material	-	
3 Bottom cover		
Thickness	-	mm
Material	AS Fabric	
Colour	Natural	
Surface	Textured	
Hardness	0	°ShA



PROFILES APPLICATION

Profiles on top cover	Yes
Profiles on bottom cover	Yes
Runer sidewalls	No

SPECIAL CHARACTERIST.

AsB Antistatic Bottom Cover

TENSIONS


	N/mm
Breaking load	60
Working load 1% elong.	5
Max. load at 1.5% elong.	7

SUPPORT SURFACE

Slider bed	Yes
Rollers	Yes
Trough application	No

MIN. DRUM DIA.

mm



Flexing (F)	20
Back flexing (C)	40

FRICTION COEFF. BOTTOM COVER

On steel Din./Est.	0.16 / 0.23
On wood Din./Est.	0.13 / 0.21
On plastic Din./Est.	0.14 / 0.21

FASTENERS


25LL

REMARKS

Longitudinal splice	No
Max. manufacturing width	3000 mm
Last modified	2015.12.21

SPLICING PARAMETERS

Splice	Pressure Kp/cm2	Sup. Temp. °C	Inf. Temp. °C	Min Time	Top Cov. Flomil/ Film	Intern. Flomil	Sheet
DS/2	2.50	170	170	8	Film CN01	-	18



The splice parameters are for orientation only as they depend on the type of press and the thickness of the plates used.

We recommend carrying out a trial run with pieces of the same belt before splicing the belt itself.

Time starts when the press has reached the stated temperature.

www.bondspowertransmission.com | all right reserved