
BND001PTB193
Data Sheet

BONDS®

STRUCTURE

Total Thickness	4.00	mm
No. of Plies	2	
Fabric	Polyester	
Weft	Rigid	
Weight	5.00	kg/m2
Constant Temp. ºC	- 5 / 80	
Intermittent Tem. ºC	- 15 / 100	
1 Top cover		
Thickness	1.00	mm
Material	PVC	
Colour	Black 04	
Surface	Smooth	
Hardness	76	°ShA
2 Internal cover		
Material	PVC	
3 Bottom cover		
Thickness	1.00	mm
Material	PVC	
Colour	Black 04	
Surface	Smooth	
Hardness	76	°ShA



PROFILES APPLICATION

Profiles on top cover	Yes
Profiles on bottom cover	Yes
Runer sidewalls	Yes

SPECIAL CHARACTERIST.

As Antistatic

TENSIONS


	N/mm
Breaking load	80
Working load 1% elong.	8
Max. load at 1.5% elong.	12

SUPPORT SURFACE

Slider bed	No
Rollers	Yes
Trough application	No

MIN. DRUM DIA.

mm



Flexing (F)	75
Back flexing (C)	75

FRICTION COEFF. BOTTOM COVER

On steel Din./Est.	- / -
On wood Din./Est.	- / -
On plastic Din./Est.	- / -

FASTENERS


1A, MR1, RS-62, UX1SP


REMARKS

Longitudinal splice	Yes
Max. manufacturing width	3000 mm
Last modified	2017.02.17

SPLICING PARAMETERS

Splice	Pressure Kp/cm2	Sup. Temp. ºC	Inf. Temp. ºC	Min Time	Top Cov. Flomil/ Film	Intern. Flomil	Sheet
DE	2.00	175	175	6	FNG01	ING00	1
DG	2.00	175	175	6	FNG01	ING00	3





The splice parameters are for orientation only as they depend on the type of press and the thickness of the plates used.

We recommend carrying out a trial run with pieces of the same belt before splicing the belt itself.

Time starts when the press has reached the stated temperature.

www.bondspowertransmission.com | all right reserved