
BND001PTB265
Data Sheet

BONDS®

STRUCTURE

Total Thickness	2.50	mm
No. of Plies	2	
Fabric	Polyester	
Weft	Rigid	
Weight	3.20	kg/m2
Constant Temp. ºC	- 10 / 80	
Intermittent Tem. ºC	- 15 / 100	
1 Top cover		
Thickness	0.90	mm
Material	PVC	
Colour	Black 01	
Surface	Mat	
Hardness	82	°ShA
2 Internal cover		
Material	PVC	
3 Bottom cover		
Thickness	-	mm
Material	Silent Fabric	
Colour	Natural	
Surface	Textured	
Hardness	0	°ShA



PROFILES APPLICATION

Profiles on top cover	Yes
Profiles on bottom cover	Yes
Runer sidewalls	Yes

SPECIAL CHARACTERIST.

As	Antistatic Top Cover
FL	Flame Retardant ISO340
SF	Silent Fabric

TENSIONS


	N/mm
Breaking load	180
Working load 1% elong.	17
Max. load at 1.5% elong.	25

SUPPORT SURFACE

Slider bed	Yes
Rollers	Yes
Trough application	No

MIN. DRUM DIA.

mm



Flexing (F)	40
Back flexing (C)	60

FRICTION COEFF. BOTTOM COVER

On steel Din./Est.	0.15 / 0.20
On wood Din./Est.	0.16 / 0.24
On plastic Din./Est.	0.15 / 0.26

FASTENERS


1A, MR1, RS-62, UX1SP


REMARKS

Longitudinal splice	Yes
Max. manufacturing width	3000 mm
Last modified	2017.02.20

SPLICING PARAMETERS

Splice	Pressure Kp/cm2	Sup. Temp. ºC	Inf. Temp. ºC	Min Time	Top Cov. Flomil/ Film	Intern. Flomil	Sheet
DE	2.00	175	175	9	FNG01/1	ING00	1
DS/2	2.50	170	165	12	Film CN02	-	18





The splice parameters are for orientation only as they depend on the type of press and the thickness of the plates used.

We recommend carrying out a trial run with pieces of the same belt before splicing the belt itself.

Time starts when the press has reached the stated temperature.

www.bondspowertransmission.com | all right reserved